

S-TIH 6

Code(d) **805254**

Code(e) **813252**

Refractive Index n_d	Abbe Number v_d	Dispersion $n_F - n_C$
1.80518	25.4	0.03166
1.805181	25.42	0.031669
Refractive Index n_e	Abbe Number v_e	Dispersion $n_F' - n_C'$
1.812641	25.22	0.032223

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.74917
n_{1970}	1.97009	1.75558
n_{1530}	1.52958	1.76321
n_{1129}	1.12864	1.77160
n_t	1.01398	1.77495
n_s	0.85211	1.78151
$n_{A'}$	0.76819	1.78643
n_r	0.70652	1.79118
n_C	0.65627	1.79611
$n_{C'}$	0.64385	1.79752
$n_{\text{He-Ne}}$	0.6328	1.79885
n_D	0.58929	1.80491
n_d	0.58756	1.80518
n_e	0.54607	1.81264
n_F	0.48613	1.82777
$n_{F'}$	0.47999	1.82974
$n_{\text{He-Cd}}$	0.44157	1.84460
n_g	0.435835	1.84729
n_h	0.404656	1.86494
n_i	0.365015	

Partial Dispersions	
$n_C - n_t$	0.021155
$n_C - n_{A'}$	0.009673
$n_d - n_C$	0.009075
$n_e - n_C$	0.016535
$n_g - n_d$	0.042105
$n_g - n_F$	0.019511
$n_h - n_g$	0.017653
$n_i - n_g$	
$n_C - n_t$	0.022564
$n_e - n_{C'}$	0.015126
$n_{F'} - n_e$	0.017097
$n_i - n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6680
$\theta_{C,A'}$	0.3054
$\theta_{d,C}$	0.2866
$\theta_{e,C}$	0.5221
$\theta_{g,d}$	1.3295
$\theta_{g,F}$	0.6161
$\theta_{h,g}$	0.5574
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7002
$\theta'_{e,C'}$	0.4694
$\theta'_{F',e}$	0.5306
$\theta'_{i,F}$	

Thermal Properties	
Strain Point StP (°C)	571
Annealing Point AP (°C)	587
Transformation Temperature Tg (°C)	604
Yield Point At (°C)	630
Softening Point SP (°C)	690
Expansion Coefficients (-30~+70°C)	89
α (10 ⁻⁷ /°C) (+100~+300°C)	107
Thermal Conductivity k (W/m·K)	1.011

Coloring			
λ_{80}	44	λ_5	37
λ_{70}			

Internal Transmittance	
$\lambda(\text{nm})$	$\tau_{10\text{mm}}$
280	
290	
300	
310	
320	
330	
340	
350	
360	
370	0.12
380	0.48
390	0.70
400	0.82
420	0.919
440	0.955
460	0.970
480	0.978
500	0.984
550	0.993
600	0.995
650	0.994
700	0.996
800	0.998
900	0.998
1000	0.998
1200	0.998
1400	0.997
1600	0.995
1800	0.986
2000	0.978
2200	0.958
2400	0.928

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0021
$\Delta\theta_{C,A'}$	-0.0012
$\Delta\theta_{g,d}$	0.0176
$\Delta\theta_{g,F}$	0.0158
$\Delta\theta_{i,g}$	

Mechanical Properties	
Young's Modulus E (10 ⁸ N/m ²)	931
Rigidity Modulus G (10 ⁸ N/m ²)	369
Poisson's Ratio σ	0.261
Knoop Hardness Hk[Class]	540 5
Abrasion Aa	191
Photoelastic Constant β (nm/cm/10 ⁵ Pa)	2.81

Constants of Dispersion Formula	
A ₁	1.77227611E+00
A ₂	3.45691250E-01
A ₃	2.40788501E+00
B ₁	1.31182633E-02
B ₂	6.14479619E-02
B ₃	2.00753254E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	1 ~ 2
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Other Properties	
Bubble Quality Group B	
Specific Gravity d	3.37
Remarks	

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dt relative (10 ⁻⁶ /°C)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	-0.6	0.3	0.4	0.7	1.3	2.6	4.1
-20~0	-0.6	0.4	0.5	0.9	1.5	2.8	4.4
0~20	-0.5	0.5	0.6	1.0	1.6	3.0	4.8
20~40	-0.4	0.7	0.8	1.2	1.8	3.3	5.1
40~60	-0.4	0.8	0.9	1.3	2.0	3.5	5.5
60~80	-0.3	0.9	1.0	1.5	2.1	3.8	5.8